



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

TECHNICAL DATA SHEET

CHAMÄLEON RUST PROTECTIVE PRIMER

Article number:	26002, 26003, 26004
Intended use:	Car refinishing Product/ Primer, Anticorrosion additive
General characteristics:	For the treatment of surfaces, treated and untreated, of wood, metal, aluminium, glass, stone and various types of plastic. Suitable primer as pre treatment for re-spraying with all lacquer systems (alkyd resin, nitro cellulose, 1-K acrylic and 2-K acrylic lacquers).
Product characteristics:	<ul style="list-style-type: none">▪ Fast drying▪ Excellent coverage and filling property▪ Corrosion preventive▪ Easy to sand, both wet and dry (from grain 400)▪ Re-sprayable with all lacquer systems
Technical characteristics:	
Contents:	500 ml
Colour:	Grey
Base:	Nitro-cellulose binder
VOC-content:	Approximately 85% w/w
Solid content:	Approximately 15% w/w
Coverage:	1,5 to 2 m ² Approximately 0,5 m ²
Dust dry:	After 5 to 10 minutes
Tack free:	After 10 to 20 minutes
Hardened/re-sprayable:	After 2 hours
Heat resistant:	To 110°C



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

Usage:

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment:

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

Treatment:

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Application:

Apply the primer in several thin layers. Before applying the next layer, again shake the aerosol.

After use:

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

*For the additional information that is not included to the Technical Data Sheet apply to the supplier:
e-mail: info@chamaeleon-produktion.de*

See information on safety in Safety Data Sheet.

Chamäleon GmbH – Technical Data Sheet



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>