



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

TECHNICAL DATA SHEET

CHAMÄLEON ACRYLIC AEROSOL CLEAR COAT

Article number:	26404
Intended use:	Car refinishing Product/ Preparation
General characteristics:	High quality clear varnish to treat surfaces, treated and untreated, of wood, metal, aluminum, glass, stone, and various types of plastic.
Product characteristics:	<ul style="list-style-type: none">• Fast drying• Excellent filling property• Lasting gloss• Scratch free and shock proof• Resistant to weather influences• Corrosion preventive• UV-resistant and non-fading• Excellent adhesion

Physical and Chemical

Characteristics

Contents	500 ml
Base	Acrylic resin
Colour	Transparent
VOC-content	Approximately 90% w/w
Solid content	Approximately 10% w/w
Gloss	High gloss
Coverage	1,5 to 2 m ²
Dust dry	After approximately 60 minutes
Tack free	After 10 to 20 minutes
Hardened/re-sprayable	After 2 hours
Heat resistant	To 110°C

Usage:

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment:

The surface should be clean, dry and free of grease. Slightly sand the surface (grain 600).



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

Treatment:

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the clear varnish in several thin layers. Before applying the next layer, again shake the aerosol.

After use:

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

*For the additional information that is not included to the Technical Data Sheet apply to the supplier:
e-mail: info@chamaeleon-produktion.de
See information on safety in Safety Data Sheet.*