



Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon/produktion.de](mailto:info@chamaeleon/produktion.de)  
<http://www.chamaeleon/produktion.de>

## *TECHNICAL DATA SHEET*

### CHAMÄLEON GRAVEX SPRAY

- Article number:** 37014 (White), 37024 (Grey),  
37034 (Black)
- Intended use:** Car refinishing Product/ Preparation
- General characteristics:** High quality sprayable preservative against chippings to treat the underside and visible parts of the motor vehicles.
- Product characteristics:**
- Re-sprayable with all lacquer systems
  - Remains flexible
  - Very good adhesion
  - Resistant to weather influences
  - Resistant to weak acids and bases
  - Excellent corrosion prevention
  - Sound-absorbing
- Technical characteristics:**
- Contents:** 500 ml
- VOC-content:** Approximately 74% w/w
- Dust dry:** After approximately 30 minutes
- Tack free:** After approximately 60 minutes
- Re-sprayable:** After 2 hours
- Usage:**
- Before use, carefully read the directions on the packaging and act accordingly.
- Pre Treatment:** Remove loose old lacquer and rust and sand the surface.
- Treatment:** The surface should be clean, dry and free of grease. The aerosol should have room



Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon/produktion.de](mailto:info@chamaeleon/produktion.de)  
<http://www.chamaeleon/produktion.de>

**After use:**

temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the Chamaeleon Aerosol anti gravel coating in several layers. After drying, without sanding, re-sprayable with all lacquer systems.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

*For the additional information that is not included to the Technical Data Sheet apply to the supplier:  
e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)  
See information on safety in Safety Data Sheet.*